


## 995 Blocked Accelerator

### FOR PROFESSIONAL USE ONLY

Description
-------------

The 995 Blocked Accelerator is an additive to help extend potlife and promote faster cure times. 995 Blocked Accelerator may be used with any Utech Urethane topcoat or Clear to promote faster tape and dry times, while improving the overspray absorption during application



First prepare the topcoat or clearcoat according to the Technical Data Sheet. Then add 995 Blocked Accelerator:

- up to 2-3 ounces per RTS Gallon
- up to 15-20 Grams per RTS Quart



See Technical Data Sheet of the Topcoat or Clearcoat



See Technical Data Sheet of the Topcoat or Clearcoat



Between coats  
10-15 minutes at 70°F (20°C)



See Technical Data Sheet of the Topcoat or Clearcoat



Use suitable respiratory protection  
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator

Read complete TDS for detailed product information



## 995 Blocked Accelerator

### FOR PROFESSIONAL USE ONLY

#### Description

The 995 Blocked Accelerator is an additive to help extend potlife and promote faster cure times. 995 Blocked Accelerator may be used with any Utech Urethane topcoat or Clear to promote faster tape and dry times, while improving the overspray absorption during application

#### Product and additives

Product 995 Blocked Accelerator

#### Basic raw materials

995 Blocked Accelerator: Special catalysts and additives

#### Suitable Applications

995 Blocked Accelerator is best used between 70°F and 90°F in:

- All U-Tech single stage topcoats
- All U-Tech clearcoat

**NOTE:** 995 Blocked Accelerator is not suitable for use in:

- Polybase or Polybase Plus basecoats
- Wet on Wet Sealers

#### Mixing Ratio



First prepare the topcoat or clearcoat according to the Technical Data Sheet.

Then add 995 Blocked Accelerator:


- up to 2-3 ounces per RTS Gallon
- up to 15-20 Grams per RTS Quart

#### Application process



See Technical Data Sheet of the Topcoat or Clearcoat

#### Flash off



10 minutes between coats

#### VOC

995 Blocked Accelerator

8.1 lb/gal

969 g/liter

#### Product storage

Store products unopened, and used products with closed lids preferably between 60°F-95°F (10°C-35°C)  
Avoid too much temperature fluctuation, optimal storage temperature approximately 70°F (20°C)

- 995 Blocked Accelerator: 12 months



## 995 Blocked Accelerator

**FOR PROFESSIONAL USE ONLY**

---

**FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coating brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

**Head Office**

Akzo Nobel Car Refinishes Inc. 5555 Spalding Drive Norcross, GA 30092, USA. [www.akzonobelcarrefinishes.net](http://www.akzonobelcarrefinishes.net)