

T890 Flattening Agent

FOR PROFESSIONAL USE ONLY

Description

890 Flattening Agent is an additive that flattens topcoats and clearcoats. 890 Flattening Agent may be used in all U-Tech single stage colors and clearcoat systems.



Mix the single stage color/clearcoat by weight with the desired percentage of 890 Flattening Agent.


After stirring, continue with TDS recommended mixing ratio



See Technical Data Sheet of the Topcoat or Clearcoat



See Technical Data Sheet of the Topcoat or Clearcoat



See Technical Data Sheet of the Topcoat or Clearcoat



See Technical Data Sheet of the Topcoat or Clearcoat



Use suitable respiratory protection

Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator

Read complete TDS for detailed product information



T890 Flattening Agent

FOR PROFESSIONAL USE ONLY

Description

890 Flattening Agent is an additive that flattens topcoats and clearcoats. 890 Flattening Agent may be used in all U-Tech single stage colors and clearcoat systems.

Product and additives

Product 890 Flattening Agent

Basic raw materials

890 Flattening Agent: Hydroxy acrylic resins

Suitable Applications

- 890 Flattening agent may be used in
- All U-Tech single stage topcoats
 - All U-Tech clearcoat

Mixing Ratio



890 Flattening Agent can be used at many desired gloss levels in any U-Tech intermix single stage system and clearcoats. Below is a chart describing the gloss level in GU (gloss units). It is recommended to prepare a sprayout sample to determine the desired gloss

Gloss Level	% of 890 Flattening Agent added to color or clear
High (70-80 gu)	10%
Eggshell (50-60 gu)	20%
Semi gloss (40-50 gu)	30%
Matt (20-30 gu)	40%
Flat (10-20 gu)	50%

Mix the single stage color or clearcoat by weight with the desired percentage of 890 Flattening Agent. After thorough stirring of this mixture, continue by adding the activator and reducers for the product being used.

NOTE: A spray out should be done first to determine desired gloss level.

Application process



See Technical Data Sheet of the Topcoat or Clearcoat

VOC

890 Flattening Agent

6.2 lb/gal

754 g/liter

Product storage

Store products unopened, and used products with closed lids preferably between 60°F-95°F (10°C-35°C)
Avoid too much temperature fluctuation, optimal storage temperature approximately 70°F (20°C)

- 890 Flattening Agent: 2 years



T890 Flattening Agent

FOR PROFESSIONAL USE ONLY

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coating brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes Inc. 5555 Spalding Drive Norcross, GA 30092, USA. www.akzonobelcarrefinishes.net